Ismail Industries Limited



Version: 1 (2021)

TECHNICAL DATA SHEET

BOPET FILM Transparent

Untreated

Product Code: APB-P(U)

Product Description:

Astro Films APB-P(U) is a transparent co-extruded BOPET film, with both sides un-treated.

Application:

- · Tape, Stationery
- Release liners, Transfer films

Key Features:

- Good Gloss and Clarity
- Good Handling Properties
- Consistent Machinability
- · High Dimensional Stablility

PROPERTIES			TEST METHOD (ASTM)	UNIT	TYPICAL VALUE
THICKNESS			Internal	Micron	19
DEVIATION OF AVG. FILM THICKNESS					-
FILM DENSITY			D-1505	gm/cc	1.4
GRAMMAGE			Internal	gm/m ²	26.6
YIELD			Internal	m²/kg	37.59
TREATMENT LEVEL	•		D-2578	dyne/cm	52
COEFF OF FRICTION		DYNAMIC	D-1894	-	0.5 ± 0.02
HAZE			D-1003	%	4.0
		MD*		Kg/cm ²	2,000
TENSILE STRENGTH AT BREAK		TD*	D-882		2,200
		MD*		(Psi)	28,400
ELONGATION AT BREAK		TD*			31,300
		MD*	D-882	%	110
UEAT CURINIVA CE		TD*			85
HEAT SHRINKAGE		MD*	D-1204	%	3.0
(AT 150°c AND 30MIN)		TD*			0.5
W.V.T.R (38°c & 90% RH)			F-1249	gm/m²/day	28
				(gm/100in ² /day)	1.8
O.T.R (23°c & 0% RH)			D-3985	cc/m²/day	80
,				(cc/100in²/day)	5.2

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

Storage

It is recommended to store the film below 30°C in order to avoid deterioration of film properties. It is advisable to use the material on FIFO basis.

Food Contact

Complies with FDA and EC regulations. MSDS are available on request.

Disclaimer

Information contained here is best to our knowledge but limited to the information as specified. No representation or warranty is made regarding the information or its fitness to a particular use. The user is solely responsible for all determinations regarding use and we disclaim liability for any loss or damage that may occur from the use of this information. Astro Films reserves the right to change the technical data sheet at any time for enhancing the Quality of the products without prior information.