

Stability

directions

Key Features

• Excellent Dimensional

 Excellent Clarity and Transparency

 Excellent Mechanical and Thermal properties
 Uniform Strength in all BOPET FILM
Transparent Isotropic
APB-IST

Is a transparent co-extruded BOPET film, with one side Corona treated and other side untreated. Film provides excellent isotropic characteristics.

Application

Recommended for Lidding application of cups, trays, dairy, cosmetics & pharmaceutical products
Packaging, Printing and Lamination

Corona Treated Layer	
Core Layer	
Untreated Layer	. 7

PROPERTIES		TEST METHOD (ASTM)	UNIT	TYPICAL VALUE
THICKNESS		Internal	Micron	12
DEVIATION OF AVG. FILM THICKNESS			%	± 1.5
FILM DENSITY		D-1505	gm/cc	1.4
GRAMMAGE		Internal	gm/m²	16.8
YIELD		Internal	m²/kg	59.52
TREATMENT LEVEL	CORONA	D-2578	dyne/cm	52
COEFF OF FRICTION	DYNAMIC	D-1894	-	0.50 ± 0.02
HAZE		D-1003	%	2.0
GIOSS (NOVA GLOSS)		D-1003	%	110
	MD*		Kg/cm²	2300 -2500
TENSILE STRENGTH AT BREAK	TD*	D-882	Kg/CIII	2600 -2900
TENSILE STRENGTH AT BREAK	MD*		(Psi)	32,700 - 35,500
	TD*			36,900 - 41,000
ELONGATION AT BREAK	MD*	D-882	%	110 - 116
ELONGATION AT BREAK	TD*	D-882		90 - 95
RATIO OF TS (+45/-45)		Internal	-	0.60 - 1.4
RATIO OF ELONGATION (+45/-45)		IIIterriai		0.60 - 1.8
HEAT SHRINKAGE	MD*	D-1204	%	≤2.5
(AT 150°C AND 30MIN)	TD*	D-1204	/0	≤ 0.5
W.V.T.R (38°C & 90% RH)		F-1249	gm/m²/day	45
W.V.T.N (38 C & 30% NH)		1-1249	(gm/100in ² /day)	2.9
O.T.R (23°C & 0% RH)		D-3985	cc/m²/day	110
0.1.N (23 C & 0/0 NH)			(cc/100in²/day)	7.0

^{*}MD = Machine Direction *TD = Transverse Direction

Reel Packing Format

Core Size	Outer Reel Dia
3" (76 mm)	< 550 mm
6" (152 mm)	< 650 mm

Min Reel Size	Max Reel Size
400 mm	2200 mm
400 111111	2200 111111

Storage

It is recommended to store the film below 30°C in order to avoid deterioration of film properties. It is advisable to use the material on FIFO basis.

Food Contact

Complies with FDA and EC regulations. MSDS are available on request.

Disclaimer

Information contained here is best to our knowledge but limited to the information as specified. No representation or warranty is made regarding the information or its fitness to a particular use. The user is solely responsible for all determinations regarding use and we disclaim liability for any loss or damage that may occur from the use of this information. Astro films reserves the right to change the technical data sheet at any time for enhancing the Quality of the products without prior information.

