


CPP FILM Transparent Heat Sealable + Corona

Is a Low COF transparent Cast Polypropylene (CPP) film with both sides heat sealable and one side treated.

Key Features

- Excellent Optical Properties
- Good Machinability
- Low COF
- Good Hot Tack
- **Good Seal Integrity**



Application

Printing and Lamination

Suitable for high speed packaging which requires low COF properties General purpose printing and pouching of bakery products

Properties		Test Method (ASTM)	Unit	Typical Value		
THICKNESS		Internal	Micron	25	30	40
		IIILEITIAI				
DEVIATION of AVG FILM THICKNESS			%	± 5	± 5	± 5
FILM DENSITY		D-1505	gm/cc	0.9	0.9	0.9
GRAMMAGE		Internal	gm/m ²	22.5	27.0	36
YIELD		Internal	m²/kg	44.4	37.04	37.04
TREATMENT LEVEL		D-2578	dyne/cm	≥38	≥38	≥38
COEFF OF FRICTION (Film x Metal)	DYNAMIC	D-1894	-	≤ 0.18	≤ 0.18	0.2
HAZE		D-1003	%	2.5	2.5	3.5
GLOSS		D-2457	Unit	122	122	115
TENSILE STRENGTH AT BREAK	MD*	D-882	Kg/cm ²	550	555	500
	TD*			250	250	210
	MD*		(Psi)	7,200	7,200	7,100
	TD*			3,400	3,400	2,800
ELONGATION AT BREAK	MD*	D-882	%	550	550	570
	TD*			600	650	670
HEAT SEAL INITIATION TEMPERATURE		INTERNAL	° C	120	120	120
HEAT SEAL STRENGTH (AT 135° C)			gm/25mm	1,300	1,200	1,200
W.V.T.R.(38°C & 90%RH)		F-1249	gm/m²/day	11	11	9
			(gm/100in ² /day)	0.7	0.7	0.6
O.T.R. (23°C & 0% RH)		D-3985	cc/m ² /day	3,600	3,550	3,500
			(cc/100in²/day)	230	230	229

^{*}MD = Machine Direction *TD = Transverse Direction *38 dyne/cm guaranteed for 3 months from date of delivery

Reel Packing Format

Core Size	Outer Reel Dia		
3" (76 mm)	< 550 mm		
6" (152 mm)	< 650 mm		

Min Reel Size	Max Reel Size	
400 mm	2200 mm	

Storage

It is recommended to store the film below 30°C in order to avoid deterioration of film properties. It is advisable to use the material on FIFO basis.

Food Contact

Complies with FDA and EC regulations. MSDS are available on request.

Disclaimer

Information contained here is best to our knowledge but limited to the information as specified. No representation or warranty is made regarding the information or its fitness to a particular use. The user is solely responsible for all determinations regarding use and we disclaim liability for any loss or damage that may occur from the use of this information. Astro films reserves the right to change the technical data sheet at any time for enhancing the Quality of the products without prior information.